



Blend of plant oils and gum resin for the protection of wooden floors.

INGREDIENTS

Linseed oil, gum resin, and plant oils, essential oils, lead-free driers.

Note: Natural products are not odour and emission free. Consider possible allergies!

AREA OF USE

For the impregnation and protection of all wooden floors. A treatment with **ProNature Floor** will maintain the wood moisture balance ("wood can breathe") and such creates a pleasant room climate. Also suitable for Cork flooring i.e. tiles etc.

GENERAL

For reasons of environmental safeness and ease of restoration wooden floors should not be "sealed". Even though the hardness of two component synthetic coatings can not be achieved with natural coatings, synthetic coatings are also not entirely safe from scratching and wear and can only be repaired by complete removal and recoating.

Natural coatings have the added advantage not to contain any ingredients, which could cause harmful emissions, like formaldehyde or aromatic solvents, which could increase the risk of cancer.

COVERAGE

Approximately 9 – 14 m²/liter, depending on wood type.

SURFACE PREPARATION

Clean surface and sand wood to a fine, smooth finish using grit i.e.100, preferably finer. Surface must be dry, clean and dust-free.

APPLICATION

Stir material well before application. **ProNature Floor** is applied liberally using a brush or short bristle paint roller until saturation is reached. **In order to avoid glossy spots and prolonged drying it is important to remove and dry off any excess thoroughly that has not been absorbed after about 10-15 min using a lint-free cloth or a floor-polishing machine leaving a surface dry to the touch.** Leave to dry for 4-6 hrs.

A light sanding after drying is recommended using a floor polishing machine with medium coarse pad or sanding paper grit 220. Then thinly apply second coat of **ProNature Floor**. **Remove any excess thoroughly that has not been absorbed directly after application using a lint-free cloth or a floor-polishing machine (soft pad) leaving a surface dry to the touch.**

Allow drying for a minimum of 12 hrs.

If a third coat is desired, proceed as described above.

! Cold weather and high humidity will retard the drying process!

CLEANING, CARE and REPAIR

The durability of an oiled wooden floor highly depends on regular cleaning and care. For the first two weeks floors should not be cleaned wet but only swept. Thereafter floors are cleaned with a neutral soap solution and wiped with a damp cloth only.

ProNature Floor should receive aftercare with **ProNature Floor Care Oil** or **ProNature Wax Balm** in regular intervals at least three times a year. Apply sparingly and polish after a drying time of approx. 1hr.

ProNature Floor is spot repairable and should small damages from wear or scratching occur just clean the area thoroughly using **ProNature Plant Turpentine** where necessary, and sand concerned area lightly with steel wool or fine scouring pad. Remove dust and apply a thin layer of **ProNature Floor** with a soft cloth. Remove excess and leave to dry for approx. 12 hrs. The treated area should not be walked on for 48 hours.

GENERAL INFORMATION

ProNature Floor is ready to use and needs not be diluted. Depending on the wood type a thinning down of the first coat with about 10 % of **ProNature Plant Turpentine** may be required. Clean brushes and equipment with **ProNature Plant Turpentine**.

SAFETY PRECAUTIONS

Caution: Product is ignitable! Soaked, used cloths may spontaneously combust, and should be spread open, or kept safely in a tightly sealed tin after use.

PACKAGE SIZES

0,5 l, 1 l, 5 l and 25 l

STORAGE STABILITY

A minimum of 12 months in unopened containers when stored in a cool and dry place.

General

The above information given is intended as a guideline only. Since this product is used outside of our control, EnviroTouch CC cannot be held liable for any loss or damage whatsoever relating to the application or surface it is applied to. We reserve the right to change specifications at any time and without prior notice. **Last revised: 05/2008**